



**MAZZONETTO Spa**  
Via A. Ceccon, 10 - 35010 Loreggia (PD)  
t. +39 049 9322611 - f. +39 049 9322650  
mazzonetto@mazzonettometalli.it  
www.mazzonettometalli.it



pre-painted aluminum VESTIS / SURFACES



<b>Reference standard:</b>	
UNI EN 1396, UNI EN 573-3, UNI EN 485, UNI EN 13523, UNI EN 13501	
<b>Technical features:</b>	
Base metal	Aluminium 99,5%
Alloy type	Alloy series 3000
Temper	H41
<b>FRONT SIDE</b> coating	35 µm K2 surface (+/- 3 µm)
<b>BACK SIDE</b> coating	25 µm super-polyester
Colors	Copper Roof - Green Roof – Grey Roof – Testa di Moro RAL 7016 – RAL 9006 – RAL 7037 – RAL 9002 – Black Grafite – Agate Grey – Slate Grey – Quartz Grey
Brilliance	- Copper Roof - Green Roof – Grey Roof: 15 GU - Testa di Moro RAL 7016 – RAL 9006 – RAL 7037 – RAL 9002: 30 GU - Black Grafite – Agate Grey – Slate Grey – Quartz Grey: 5 GU
Reaction to fire classification	A1
<b>Chemical composition:</b>	
Manganese (Mn)	1,0 – 1,5 %
Magnesium (Mg)	0,2 – 0,6 %
Iron (Fe)	0,7 %
Silicon (Si)	0,6 %
<b>Mechanical properties:</b>	
Tensile strength	130 – 180 Mpa
Elongation	8,00 % min.
Cracking resistance in bending (bend testing)	≤ 1,5 T
Coating adhesion	≤ 1,0 T
Surface hardness "pencil"	H
Corrosion Resistance	hours salt spray test: 1500 h
UV resistance	Test QUV 2000 h Class of UV resistance: RUV4
<b>Dimensional characteristics:</b>	
Standard thickness	0.70 mm
Standard widths	500 mm – 650 mm – 1300 mm
Coil weight	from 50 to 3000 kg
<b>Applications:</b>	
Profiling, bending, calendering according to UNI EN 612	
<b>Use:</b>	
Civil and industrial building industry	



## vestis

prepainted aluminum VESTIS / 3D SURFACES

<b>Reference standard:</b>	
UNI EN 1396, UNI EN 573-3, UNI EN 485, UNI EN 13523, UNI EN 13501	
<b>Technical features:</b>	
Base metal	Aluminium 99,5%
Alloy type	Alloy series 3000
Temper	H44
<b>FRONT SIDE</b> coating	35 µm 3D surface (+/- 3 µm)
<b>BACK SIDE</b> coating	25 µm super-polyester
Colors	Grigio Dolomiti – Ral 7016 – Ral 7037 - Cortex
Brilliance	Grigio Dolomiti – Ral 7016 – Ral 7037 - Cortex: 5 GU
Reaction to fire classification	A1
<b>Chemical composition:</b>	
Manganese (Mn)	1,0 – 1,5 %
Magnesium (Mg)	0,2 – 0,6 %
Iron (Fe)	0,7 %
Silicon (Si)	0,6 %
<b>Mechanical properties:</b>	
Tensile strength	130 – 180 Mpa
Elongation	3,00 % min.
Cracking resistance in bending (bend testing)	≤ 1,5 T
Coating adhesion	≤ 1,0 T
Surface hardness "pencil"	H
Corrosion Resistance	salt spray test: 1500 h
UV resistance	Test QUV 2000 h Class of UV resistance: RUV4
<b>Dimensional characteristics:</b>	
Standard thickness	Grigio Dolomiti: 1000X0,80 – 1250X0,80 – 1000X1,00 – 1250X1,00 Ral 7016: 1000X0,80 – 1250X0,80 Ral 7037: 1000X0,80 – 1250X0,80 – 1000X1,00 Cortex: 1000X0,80 – 1250X0,80 – 1000X1,00 – 1250X1,00
Standard widths	1000 mm – 1250 mm - All widths on request
Coil weight	from 50 to 3000 kg
<b>Applications:</b>	
Profiling, bending, calendering according to UNI EN 612	
<b>Use:</b>	
Civil and industrial building industry	